

**IN THE CLAIMS**

*This listing of claims will replace all prior versions and listings of claims in the application.*

**Listing of Claims:**

1. (Currently Amended) A Bismuth glass composition comprising 0.5 to 14 wt% of SiO<sub>2</sub>, 3 to 15 wt% of B<sub>2</sub>O<sub>3</sub>, 4 to 22 wt% of ZnO, 55 to 90 wt% of Bi<sub>2</sub>O<sub>3</sub> and 4 wt% or less of Al<sub>2</sub>O<sub>3</sub>, and

further comprising 5 wt% or less of an oxide of Group A, 12 wt% or less of an oxide of Group B and 0.1 to 10 wt% of an oxide of Group C, wherein

the oxide of Group A is at least one selected from the group consisting of Li<sub>2</sub>O, Na<sub>2</sub>O and K<sub>2</sub>O,

the oxide of Group B is at least one selected from the group consisting of MgO, CaO, SrO and BaO, and

the oxide of Group C is at least one selected from the group consisting of Sc<sub>2</sub>O<sub>3</sub>, Y<sub>2</sub>O<sub>3</sub>, La<sub>2</sub>O<sub>3</sub>, CeO<sub>2</sub>, Pr<sub>2</sub>O<sub>3</sub>, Nd<sub>2</sub>O<sub>3</sub>, Sm<sub>2</sub>O<sub>3</sub>, Eu<sub>2</sub>O<sub>3</sub>, Gd<sub>2</sub>O<sub>3</sub>, Tb<sub>2</sub>O<sub>3</sub>, Dy<sub>2</sub>O<sub>3</sub>, Ho<sub>2</sub>O<sub>3</sub>, Er<sub>2</sub>O<sub>3</sub>, Tm<sub>2</sub>O<sub>3</sub>, Yb<sub>2</sub>O<sub>3</sub> and Lu<sub>2</sub>O<sub>3</sub>[[.]], and

the weight ratio of Al<sub>2</sub>O<sub>3</sub> to SiO<sub>2</sub> is 0.5 or less.

2. (Original) The bismuth glass composition in accordance with claim 1 comprising 0.5 to 12 wt% of SiO<sub>2</sub>, 3 to 9 wt% of B<sub>2</sub>O<sub>3</sub>, 4 to 19 wt% of ZnO, 55 to 85 wt% of Bi<sub>2</sub>O<sub>3</sub> and 0.1 to 4 wt% of Al<sub>2</sub>O<sub>3</sub>.

3. (Original) The bismuth glass composition in accordance with claim 1 comprising 1.7 to 12 wt% of SiO<sub>2</sub>, 3 to 9 wt% of B<sub>2</sub>O<sub>3</sub>, 9.5 to 19 wt% of ZnO, 62 to 80 wt% of Bi<sub>2</sub>O<sub>3</sub> and 0.1 to 4 wt% of Al<sub>2</sub>O<sub>3</sub>.

4. (Original) The bismuth glass composition in accordance with claim 1 comprising 1.1 to 4.5 wt% of SiO<sub>2</sub>, 4 to 9 wt% of B<sub>2</sub>O<sub>3</sub>, 9.5 to 18 wt% of ZnO and 72 to 85 wt% of Bi<sub>2</sub>O<sub>3</sub>.

5. (Original) The bismuth glass composition in accordance with any one of claims 1 to 4 comprising 4 wt% or less of the oxide of Group A.

6. (Original) The bismuth glass composition in accordance with claim 5, wherein the oxide of Group A comprises 2 wt% or less of  $\text{Li}_2\text{O}$ , 3 wt% or less of  $\text{Na}_2\text{O}$  and 4 wt% or less of  $\text{K}_2\text{O}$ .

7. (Original) The bismuth glass composition in accordance with any one of claims 1 to 3 and 5 to 6 comprising 10 wt% or less of the oxide of Group B.

8. (Original) The bismuth glass composition in accordance with claim 7, wherein the oxide of Group B comprises 5 wt% or less of  $\text{MgO}$ , 6 wt% or less of  $\text{CaO}$ , 8 wt% or less of  $\text{SrO}$  and 10 wt% or less of  $\text{BaO}$ .

9. (Original) The bismuth glass composition in accordance with any one of claims 1 to 8 comprising 0.1 to 5 wt% of the oxide of Group C.

10. (Original) The bismuth glass composition in accordance with claim 4 or 5 comprising 0.1 to 2 wt% of  $\text{Al}_2\text{O}_3$ .

11. (Original) The bismuth glass composition in accordance with 4, 5 or 10 comprising 8 wt% or less of the oxide of Group B.

12. (Original) The bismuth glass composition in accordance with claim 11, wherein the oxide of Group B comprises 2 wt% or less of  $\text{MgO}$ , 0.1 to 4.5 wt% of  $\text{CaO}$ , 0.1 to 4.5 wt% of  $\text{SrO}$  and 4 wt% or less of  $\text{BaO}$ .

13. (Original) The bismuth glass composition in accordance with any one of claims 1 to 3 and 5 to 9, wherein the weight ratio of  $\text{ZnO}$  to  $\text{B}_2\text{O}_3$  is 0.8 to 2.8.

14. (Cancelled)

15. (Currently Amended) The bismuth glass composition in accordance with any one of claims 4 to 5 [[,]] and 10 to 12 [[and 14]], wherein the weight ratio of ZnO to B<sub>2</sub>O<sub>3</sub> is 1.1 to 2.5.

16. (Currently Amended) A sealing member for a magnetic head comprising the bismuth glass composition in accordance with any one of claims 1 to 3, 5 to 9 and 13 [[to 14]].

17. (Currently Amended) A sealing member for a plasma display panel comprising the bismuth glass composition in accordance with any one of claims 4 to 5, 10 to 12 and [[14 to]] 15.

18. (Original) The sealing member for a plasma display panel in accordance with claim 17 further comprising a low-expansion ceramic filler in a weight ratio of 0.01 to 4 with respect to the bismuth glass composition.

19. (Original) The sealing member for a plasma display panel in accordance with claim 18, wherein the low-expansion ceramic filler is at least one selected from the group consisting of cordierite, willemite, forsterite, anorthite, zircon, mullite,  $\beta$ -eucryptite,  $\beta$ -spodumene, cristobalite, barium titanate, titanium oxide, tin oxide, aluminum oxide, zirconium oxide and quartz glass.

20. (Original) A magnetic head comprising a pair of magnetic core halves, at least one of which being provided with a coil groove, a magnetic gap member interposed between surfaces of the magnetic core halves facing to a magnetic gap, and the sealing member in accordance with claim 16 for bonding the pair of magnetic core halves.

21. (Original) The magnetic head in accordance with claim 20 further comprising a magnetic metal film on at least one of the surfaces facing to the magnetic gap.

22. (Original) The magnetic head in accordance with claim 20, wherein each of the paired magnetic core halves comprises a pair of nonmagnetic substrates and a magnetic metal film sandwiched between the nonmagnetic substrates.

23. (Original) A magnetic recording/reproducing device comprising the magnetic head in accordance with any one of claims 20 to 22 to perform recording and reproducing information to and from a magnetic information recording medium.

24. (Original) A plasma display panel comprising a front plate and a rear plate facing to each other, display electrodes and address electrodes arranged between the front plate and the rear plate, barrier ribs for isolating the address electrodes, dielectric layers covering the surfaces of the display electrodes and the address electrodes, respectively, and the sealing member in accordance with any one of claims 17 to 19 for bonding the peripheries of the front plate and the rear plate.

25. (Original) The plasma display panel in accordance with claim 24 provided with an air hole formed in the front plate or the rear plate, further comprising a glass tube communicating with the air hole, wherein an opening end of the air hole and an end of the glass tube are bonded with the sealing member.